

## PROBLADE™ 104R Awareness

### Pro-Blade™ Cancer-Awareness Cloth Tape

#### DESCRIPTION

Renfrew Pro™ is proud to help raise awareness and support the fight against cancer through special initiatives like Hockey Fights Cancer and Pink The Rink charities. We have developed custom Pro-Blade™ Cancer Awareness Cloth Tapes to support these causes. Specially designed for today's composite hockey sticks, this tape incorporates an advanced adhesive formulation applied to a polyester/cotton cloth base, resulting in a more substantial cloth tape with increased wear characteristics. This premium cloth tape comes in pink and purple to help teams raise awareness on the ice.

#### APPLICATIONS

- Stick handles and blades

#### PRODUCT BENEFITS

- Protect sticks from abrasion
- Helps with puck control
- Moisture resistant
- Improves grip on handle

#### TECHNICAL PROPERTIES

| Technical Property  | Nominal Value | Unit                    | Test Method    |
|---------------------|---------------|-------------------------|----------------|
| Total Thickness     | 10 (.254)     | Mils (mm)               | REN TM 20      |
| Adhesion to Steel   | 28 (7.7)      | Oz/Inch<br>(N/25mm)     | PSTC - 101 Mod |
| Adhesion to Backing | 20 (5.5)      | Oz/Inch<br>(N/25mm)     | PSTC - 101 Mod |
| Tensile Strength    | 35 (155.72)   | lbs. / inch<br>(N/25mm) | ASTM D 1000    |

## STANDARD PRESENTATIONS

- Colours: Group Shot, Bright Pink, Hockey Fights Cancer Purple

## RECOMMENDATIONS

Application to Surface: Unwind adhesive film or tape and apply the adhesive side to the mounting surface. Apply firm pressure. Recommended application temperature to achieve best results is 65°F (18°C) or above. Proper bonding may not occur unless adhesive and surface material are both at 65°F (18°C) or above.

### NOTE:

1. When applying pressure sensitive adhesive films to any surface, be sure that the surface is free from oil or other surface contaminants such as powder, dust, or release agents. Adhesive performance should be carefully checked when used on substrates containing plasticizers.
2. Shelf life is one year from date of shipment when stored in a cool dry place below 76°F (24°C). Rolls should be stored on end.