

## RENFREW HOCKEY TAPE 108R Coloured

### Polyflex Coloured Shin Pad Tape

---

#### DESCRIPTION

Our Polyflex Coloured Shin Pad tape is formulated to provide sufficient elasticity and memory to hold shin pads and other sports equipment securely in place. It allows players to skate comfortably and confidently throughout their game. This premium shin pad tape comes in 8 different colours and is also available in clear.

#### APPLICATIONS

- Shin pads

#### PRODUCT BENEFITS

- Stretchable with memory
- Waterproof polyethylene
- Enhances support
- Hand tearable
- Moisture resistant

## TECHNICAL PROPERTIES

| Technical Property  | Nominal Value | Unit                 | Test Method |
|---|---------------|----------------------|-------------|
| Adhesive Thickness (Synthetic Rubber)                                     | 2.5 ( .064mm) | Mils (mm)            | -           |
| Backing Adhesion (PSTC 101 Mod.) Initial to Backing Substrate (20 in @RT) | 35 (9.6)      | Oz/Inch (N/25mm)     | -           |
| Elongation  | 80            | %                    | -           |
| Peel Adhesion (PSTC 1 Mod./180°) Initial to S.S.(20 min. @ RT)            | 60 (16)       | Oz/Inch (N/25mm)     | -           |
| Tensile Strength  | 18 (79)       | lbs. / inch (N/25mm) | ASTM D 1000 |
| Total Thickness (excluding liner)   | 7.0 (.178)    | Mils (mm)            | -           |

## STANDARD PRESENTATIONS

- Colours: Red, Orange, Yellow, Green, Royal Blue, White, Black

## RECOMMENDATIONS

Application to Surface: Unwind adhesive film or tape and apply the adhesive side to the mounting surface. Apply firm pressure. Recommended application temperature to achieve best results is 65°F (18°C) or above. Proper bonding may not occur unless adhesive and surface material are both at 65°F (18°C) or above.

NOTE: 1. When applying pressure sensitive adhesive films to any surface, be sure that the surface is free from oil or other surface contaminants such as powder, dust, or release agents. Adhesive performance should be carefully checked when used on substrates containing plasticizers.

2. Shelf life is one year from date of shipment when stored in a cool dry place below 76°F (24°C). Rolls should be stored on end.